NEMO

ELEVATE




ELEVATE
CERAMIC WALL TILE


COLORS

MOON


BONE




PINK




GREY




BLUE



TAUPE



GRAPHITE



ENLARGED TILE PATTERN AT 100%

ELEVATE

FLOOR 12” x 24”

MOON

BONE

BLUE




GRAPHITE

ELEVATE




ELEVATE


SIZES



12” x 24”



2”x2” mosaic on 12x12” sheet



V2 Variation: Slight Variation.

ELEVATE

TECHNICAL INFORMATION

TECHNICAL CHARACTERISTICS	TEST STANDARD EN ISO	PRODUCT STANDARD ISO 13006 EN 14411	AVERAGE VALUES
DIMENSIONAL CHARACTERISTICS OF FLOOR TILE			
LENGTH AND WIDTH	10545-2	± 0,6 %	± 0,2 %
THICKNESS		± 5,0 %	8,8 ± 3,0 %
STRAIGTHNESS OF SIDES		± 0,5 %	± 0,2 %
RECTANGULARITY		± 0,5 %	± 0,2 %
SURFACE FLATNESS		± 0,5 %	± 0,2 %
PHYSICAL PROPERTIES			
WATER ABSORPTION	10545-3	≤ 0,5 %	≤ 0,1 %
BREAKING STRENGTH (N)	10545-4	MIN. 1300	2600
MODULUS OF RUPTURE (N/mm^2)		MIN. 35	50
RESISTANCE TO SURFACE ABRASION	10545-7	INDICATED BY THE MANUFACTURER	5
COEFFICIENT OF LINEAR THERMAL EXPANSION (1/K)	10545-8	TEST METHOD AVAILABLE	$6,7 \times 10^{-6}$
THERMAL SHOCK RESISTANCE	10545-9	TEST METHOD AVAILABLE	RESISTS
MOISTURE EXPANSION (mm/m)	10545-10	TEST METHOD AVAILABLE	< 0,1
CRAZING RESISTANCE	10545-11	REQUIRED	RESISTS
FROST RESISTANCE	10545-12	REQUIRED	RESISTS

TECHNICAL INFORMATION

TECHNICAL CHARACTERISTICS	TEST STANDARD EN ISO	PRODUCT STANDARD ISO 13006 EN 14411	AVERAGE VALUES
			RECTIFIED
DIMENSIONAL CHARACTERISTICS FOR WALL TILE			
LENGTH AND WIDTH	10545-2	± 0,5 %	± 0,1 %
THICKNESS		± 10,0 %	9,1 ± 3,0 %
STRAIGTHNESS OF SIDES		± 0,3 %	± 0,1 %
RECTANGULARITY		± 0,5 %	± 0,2 %
CENTRE CURVATURE		+0 ,5 % / - 0,3 %	+0 ,2 % / - 0,1 %
EDGE CURVATURE +		0,5 % / - 0,3 %	+0 ,2 % / - 0,1 %
WARPAGE		± 0,5 %	+0 ,2 %
PHYSICAL PROPERTIES			
WATER ABSORPTION	10545-3	≥ 10 %	14 %
BREAKING STRENGTH (N)	10545-4	MIN. 600	1200
MODULUS OF RUPTURE (N/mm^2)		MIN. 12	25
COEFFICIENT OF LINEAR THERMAL EXPANSION (1/K)	10545-8	TEST METHOD AVAILABLE	$7,3 \times 10^{-6}$
THERMAL SHOCK RESISTANCE	10545-9	TEST METHOD AVAILABLE	RESISTS
CRAZING RESISTANCE	10545-11R	EQUIRED	RESISTS

TECHNICAL CHARACTERISTICS		TEST STANDARD EN ISO	PRODUCT STANDARD ISO 13006 EN 14411	AVERAGE VALUES
				RECTIFIED
CHEMICAL PROPERTIES				
RESISTANCE TO HOUSEHOLD CHEMICALS AND SWIMMING POOL SALTS		10545-13	MIN. GB	GA
RESISTANCE TO LOW CONCENTRATIONS	ACIDS		TEST METHOD AVAILABLE	GLA
	ALKALIS			GLA
RESISTANCE TO HIGH CONCENTRATIONS	ACIDS		TEST METHOD AVAILABLE	GHA
	ALKALIS			GHA
RESISTANCE TO STAINS M		10545-14	IN, 3	5



NEMO

NEMOTILE.COM

ELEVATE