
### NEMO TILE + STONE GLAZED MOSAICS







## GLAZED MOSAICS HERRINGBONE

**CERAMIC** 



BLACK



CERAMIC




**BLACK** 



# GLAZED MOSAICS PENNYROUNDS

**CERAMIC** 





**BLACK** 



#### GLAZED MOSAICS CERAMIC STACK


WHITE	DANDELION	FRENCH VANILLA	JADITE	LATTE
CUMULUS	CORNFLOWER	DOVE	PEWTER	GREY MIX
RED	TWILIGHT	BLACK		




#### TECHNICAL FEATURES

		ANSI. A137.1	FACTORY	
Item	Requirement - Test	Standard	Test Result	Remark
	Method of Manufacture		Dry Pressed Tiles	
	Factory production control		ISO9001	Qualified
Dimensional and Surface Quality:		3% or 0.8mm		
	Length	±0.8mm	±0.5mm	Р
	Width	±0.8mm	±0.5mm	Р
	Straightness of sides	±1.8mm	±0.5mm	Р
	Rectangularity	±1.8mm	±0.5mm	Р
	Smoothness	±0.8mm	±0.5mm	Р
Surface	Quality			
	Visible defects of surface Water	min.95% defect free	no defect was found	Р
	Absorption	≤0.5%	≤0.1%	Р
	Breaking Strength	>250 LBF	>285 LBF	Р
	Modulus of Rupture	≥35 Mpa	≥39 Mpa	Р
	Wearing Strength	Less than 205mm³	Less than 140mm <sup>3</sup>	
	Abrasion Resistance		class IV	
	Thermal Linear Expansion	Less than 9*10 <sup>-6</sup> K <sup>-1</sup>	Less than 7*10 <sup>-6</sup> K <sup>-1</sup>	
	Thermal Shock		no defect found no	р
	Crazing Resistance		defect found no	P
	Frost Resistance		defect found 133	Р
	Bond Strength	≥50 psi	psi	Р
	Moisture Expansion		0.	0003
	Lead & Cadmium (ASTMC895)		C<0.01; L<0.05 mg/L	
	Resistance to Staining		class A	Р
	Resistance to Chemicals	Low Acids & Alkalis	class A	Р
	Resistance to Chemicals	High Acids & Alkalis	class A	Р


#### SIZE



3/4" pennyrounds mosaic on 12x12 sheet



1" Hex mosaic on 12x12 sheet



3/8" rectangle mosaic on 12x12 sheet



3/8x2" herringbone mosaic on 12x12 sheet



