

NEMO

TILE + STONE

ROCCO



ROCCO



ROCCO




ROCCO

Porcelain Tile

COLORS


Finishes: Matte, Soft, Lappato




White Small




White Medium





Beige Small





Beige Medium





Light Small




Light Medium




Dark Small




Dark Medium



Black Small


















Black Medium



ROCCO



TECHNICAL FEATURES The values in the table refer to natural (not lappato)

	Regulation	Required standards			
 Dimensions	UNI EN ISO 10545/2		Not rectified	Rectified*	
		Length and width	±0,6 % max 2mm	±0,3 % max 1mm	
		Thickness	±5 % max 0,5mm	±5 % max 0,5mm	
		Linearity	±0,5 % max 1,5mm	±0,3 % max 0,6mm	Compliant
		**Wedging	±0,5 % max 2mm	±0,3 % max 1,5mm	
* According to ISO 13006.		Warpage	±0,5 % max 2mm	±0,4 % max 1,8mm	
 Water Absorption	UNI EN ISO 10545/3	≤ 0,5 %		0,2%	
 Flexural Strength	UNI EN ISO 10545/4	≥ 35 N/mm ²		Compliant	
		S ≥ 1300 N (thickness ≥ 7,5 mm)		Compliant	
 Coefficient of restitution (COR)	UNI EN ISO 10545/5	Recommended value ≥ 0,55/		Compliant	
 Deep abrasion resistance	UNI EN ISO 10545/6	≤ 175 mm ³		Compliant	
 Abrasion resistance/	UNI EN ISO 10545/7	PEI Only for glazed tiles			
 Coefficient of thermal linear expansion	UNI EN ISO 10545/8	Tests method available/		≤ 7 · 10 ⁻⁴ C ⁻¹	
 Thermal shock resistance/Resistance	UNI EN ISO 10545/9	No sample must show visible defects		Compliant	
 Moisture expansion	UNI EN ISO 10545/10	Tests method available		≤ 0,01 % (0,1 mm/m)	
 Fire resistance/	UNI EN ISO 13501-1	Declare a value Class A1 or A ₂		A1 _s	
 Frost resistance	UNI EN ISO 10545/12	Resistant		Compliant	
 Chemical resistance	UNI EN ISO 10545/13	Resistance to household chemicals and swimming pool salts	Minimum class B (GB for glazed tiles) Minimum class B (UB for unglazed tiles)	A	
		Resistance to low concentrations of acids and alkalis	Declare a class Tests method available	LA	
		Resistance to high concentrations of acids and alkalis	Declare a class Tests method available	HA Not valid for Lappato finish.	
		Stain resistance	UNI EN ISO 10545/14	UGL Declare a value GL ≥ 3	Class 5
 Lead and cadmium discharge	UNI EN ISO 10545/15	Declared value for GL tiles			
 Assessment of slip resistance	DIN 51130	Declare a value (R)		R10 Matt	
		DIN 51097	Dichiarare un valore (A+B+C) / Declare a value (A+B+C)		A+B Matt
		BS 7976-2:2002 + A1:2013 Pendulum Friction Test	Declare a value		≥ 36 Wet Matt
 Measurement of dynamic coefficient of friction	B.C.R.A. Rep. CEC/81	Asciutto > 0,40 / Bagnato > 0,40		Asciutto > 0,40 / Bagnato > 0,40 Matt/Soft	
		ANSI A326.3 (BOT3000)	> 0,42 Wet		> 0,42 Wet Matt/Soft

Rocco MATTE and SOFT finishes are recommended for interior floors, walls and exterior walls in both residential and commercial applications. Rocco SOFT is not recommended for exterior horizontal surfaces or exterior paving, and is not recommended for ramps application. The SOFT finish is not recommended for interior floors in entrance areas if joined to outdoor commercial applications. Rocco LAPPATO is recommended for interior walls, and exterior walls in both residential and commercial applications. Rocco LAPPATO finish is not recommended for commercial floors.

SIZES



24"x24"

PACKING INFORMATION

FORMAT	SQ.FT. PER BOX	WGT. OF BOX	PEICES IN BOX	BOXES ON PALLET	SQ.FT. PER PALLET	WGT. OF PALLET
24"x24"	11.63 SQ.FT.	47.06 LB.	3	40	465.3 SQ.FT.	1,882.75 LB.



NEMO
TILE + STONE
ROCCO